

Finish - Acabado		(4x8 ft) 1.22 x 2.44 m	(4x10 ft) 1.22 x 3.06 m	(5x12 ft) 1.53 x 3.66 m	Postformability Postformabilidad
Matte- Mate	MT	●	●	●	●
Gloss - Brillante	GL/BR	●	●	●	●
Deep Line	DL	●	●	●	Z ²
Legno	LG	●	●	●	Z ²
Painted Wood	PW		●		Z ³
Split	IT		●		Z ³
Ultra Pore - Ultra Poro	UP	●	●	●	Z ³
Pore - Poro	PR	●	●		Z ³
Brush*	BS	●	*Available only in 2047, 2508, 2506 and 2507 *Disponible para las referencias 2047, 2508, 2506 y 2507		
Tessuto	TS	●			Z
Pelle	PE	●			Z
Secco	SC	●	●	●	Z ³
Cast	CA	●	●	●	Z ³
Polished	PL	●	●	●	Z ³

Z Can be postformed to a minimum 19/64" (7.5 mm) outside radius (Machine direction) for VGP and 3/8" (9.5 mm) for HGP
 Z Puede ser postformable solo en radio de 7.5 mm (19/64") o superiores en sentido longitudinal para F8 (VGP) y radio 9.5 mm (3/8") o superiores para PF10 (HGP)
 Z² Can be postformed (Machine Direction) - Postformable sólo en sentido longitudinal
 z³ Can be postformed to a minimum of ≥ 1/2" (12.5 mm) - Puede ser postformable en radio mínimo de ≥ 12.5 mm (1/2")

Standard Products - Productos Estándar

Thickness - Espesor

Horizontal Grade Standard - Grado Estándar Horizontal (F12-HGS)	0,048" (1,2 mm)
Horizontal Grade Postforming - Grado Horizontal Post-formable (PF10-HGP)	0,039" (1,0 mm)
Vertical Grade Postforming - Grado Vertical Post-formable (PF8-VGP)	0,028" (0,7 mm)
Cabinet Liner (F6 - CL)	0,020" (0,5 mm)
Backer Lam - Balance	BKL - 0,020" (0,5 mm) BKV - 0,028" (0,7 mm) BKM - 0,039" (1,0 mm) BKH - 0,048" (1,2 mm)

Special Products Productos Especiales

Thickness Espesor

Compact - Compacto	From 5/64" to 1/2" (Desde 2 mm hasta 13 mm)
EX ² Compact - EX ² Compacto	From 0.236" (6 mm) to 0.71" (18 mm)
Panelex	0.16*"; 0.24"; 0.31"; 0.39"; 0.47"; 0.59" (4*; 6; 8; 10; 12; 15 mm)
CompactSlab	0.492" (12.5 mm)
Lumiform	0.078" (2 mm) - 0.157" (4 mm)
Blindado Panel	0.295" (7,5 mm) - 0.354" (9 mm) - 0.413" (10,5 mm) - 0.452" (11,5 mm)
ChemLam	From 0.028" (0,7 mm) to 0.71" (18 mm)
Opak	0.028" - 1/2" (0,8 mm - 13 mm)
Metals - Metales	0.028" (0,7 mm) - 0.039" (1,0 mm) - 0.048" (1,2 mm)
Fired Rated - Retardante al fuego	0.028" (0,7 mm) - 1/2" (13 mm)
High Wear	0.028" (0,7 mm) - 0.039" (1,0 mm) - 0.048" (1,2 mm)
Boards - Tableros	Dry-Erase - Seco: 0.028" (0,7 mm) - 0.039" (1,0 mm) - 1/2" (13 mm) Magnetic - Magnético: 0.028" (0,8 mm) - 0.039" (1,0 mm) - 0.048" (1,2 mm) Plus: 0.028" (0,7 mm) - 0.039" (1,0 mm) - 0.048" (1,2 mm) Super: 0.028" (0,7 mm) - 0.039" (1,0 mm) - 0.048" (1,2 mm) Smart: 0.039" (1,0 mm) - 0.048" (1,2 mm)
Chalk Board - Pizarrón	0.028" (0,7 mm) - 0.039" (1,0 mm) - 1/2" (13 mm)
Chromacore	0.031" (0,8 mm) - 0.048" (1,2 mm)